

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

Claim 1 (canceled).

2. (currently amended): A corrosion resistant member comprising a base material sprayed with a corrosion resistant glass sprayed coating which is an aluminosilicate glass or zirconia silicate glass ~~containing at least one element selected from the group consisting of the group 2a, group 3a and group 4a of the periodic table of elements, wherein the corrosion resistant glass sprayed coating is the aluminosilicate glass which comprises~~ containing at least one element selected from the group consisting of elements of the group 3a of the periodic table of elements and which when expressed by an Si-Al-group 3a three-component triangular diagram, has a composition such that the atomic ratio of the respective metal elements (Si:Al:group 3a) falls within the range connecting respective points of (70:20:10), (50:20:30), (30:40:30), (30:50:20), (45:50:5) and (70:25:5).

3. (currently amended): A corrosion resistant member comprising a base material sprayed with a corrosion resistant glass sprayed coating which ~~is an aluminosilicate glass or is a zirconia silicate glass containing at least one element selected from the group consisting of the group 2a, group 3a and group 4a of the periodic table of elements, wherein the corrosion resistant glass sprayed coating is the zirconia silicate glass which comprises~~ at least one element selected from the group consisting of elements of the group 3a of the periodic table of elements and

which when expressed by an Si-Zr-group 3a three-component triangular diagram, has a composition such that the atomic ratio of the respective metal elements (Si:Zr:group 3a) falls within the range connecting respective points of (70:25:5), (70:10:20), (50:20:30), (30:40:30), (30:50:20) and (45:50:5).

4. (currently amended): A corrosion resistant member comprising a base material sprayed with a corrosion resistant glass sprayed coating which is ~~a an aluminosilicate glass or zirconia silicate glass containing at least one element selected from the group consisting of the group 2a, group 3a and group 4a of the periodic table of elements, wherein the corrosion resistant glass sprayed coating is the zirconia silicate glass which comprises at least one element selected from the group consisting of elements of the group 2a of the periodic table of elements and~~ which when expressed by an Si-Zr-group 2a three-component triangular diagram, has a composition such that the atomic ratio of the respective metal elements (Si:Zr:group 2a) falls within the range connecting-respective points of (70:25:5), (45:25:30), (30:40:30), (30:50:20) and (50:45:5).

5. (previously presented): The corrosion resistant member as claimed in claim 2, wherein an interlayer of an SiO₂-containing glass sprayed coating is provided between the base material and the corrosion resistant glass sprayed coating.

6. (previously presented): The corrosion resistant member as claimed in claim 2, wherein an interface between the base material and the corrosion resistant glass sprayed coating, or any one of interfaces among the base material, the interlayer of an SiO₂-containing glass

sprayed coating and the corrosion resistant glass sprayed coating forms a molten layer resulting from mutual melting each other.

7. (previously presented): The corrosion resistant member as claimed in claim 2, wherein the corrosion resistant glass sprayed coating has a surface roughness Ra of from 0.01 to 5 μm .

Claims 8-10 (canceled).

11. (currently amended): The corrosion resistant member according to claim 2, wherein a most superficial layer of the sprayed coating forms a spherical protruded layer in which the concentration of ~~at least one of aluminum or zirconium~~ and elements of the ~~group 2a, group 3a and group 4a~~ is lower than that of an internal sprayed coating.

12. (previously presented): The corrosion resistant member as claimed in claim 3, wherein an interlayer of an SiO_2 -containing glass sprayed coating is provided between the base material and the corrosion resistant glass sprayed coating.

13. (previously presented): The corrosion resistant member as claimed in claim 3, wherein an interface between the base material and the corrosion resistant glass sprayed coating, or any one of interfaces among the base material, the interlayer of an SiO_2 -containing glass sprayed coating and the corrosion resistant glass sprayed coating forms a molten layer resulting from mutual melting each other.

14. (previously presented): The corrosion resistant member as claimed in claim 3, wherein the corrosion resistant glass sprayed coating has a surface roughness Ra of from 0.01 to 5 μm .

15. (currently amended): The corrosion resistant member according to claim 3, wherein a most superficial layer of the sprayed coating forms a spherical protruded layer in which the concentration of ~~at least one of aluminum or zirconium~~ and elements of the ~~group 2a, group 3a and group 4a~~ is lower than that of an internal sprayed coating.

16. (previously presented): The corrosion resistant member as claimed in claim 4, wherein an interlayer of an SiO₂-containing glass sprayed coating is provided between the base material and the corrosion resistant glass sprayed coating.

17. (previously presented): The corrosion resistant member as claimed in claim 4, wherein an interface between the base material and the corrosion resistant glass sprayed coating, or any one of interfaces among the base material, the interlayer of an SiO₂-containing glass sprayed coating and the corrosion resistant glass sprayed coating forms a molten layer resulting from mutual melting each other.

18. (previously presented): The corrosion resistant member as claimed in claim 4, wherein the corrosion resistant glass sprayed coating has a surface roughness Ra of from 0.01 to 5 μm .

19. (currently amended): The corrosion resistant member according to claim 4, wherein a most superficial layer of the sprayed coating forms a spherical protruded layer in which the concentration of ~~at least one of aluminum or zirconium~~ and elements of the ~~group 2a, group 3a and group 4a~~ is lower than that of an internal sprayed coating.

20. (currently amended): A corrosion resistant member ~~comprising~~ consisting essentially of a base material sprayed with a corrosion resistant glass sprayed coating which is an

aluminosilicate glass or zirconia silicate glass containing at least one element selected from the group consisting of the group 2a, group 3a and group 4a of the periodic table of elements,

wherein an interlayer of an SiO₂-containing glass sprayed coating is provided between the base material and the corrosion resistant glass sprayed coating.

21. (previously presented): The corrosion resistant member as claimed in claim 20, wherein an interface between the base material and the corrosion resistant glass sprayed coating, or any one of interfaces among the base material, the interlayer of an SiO₂-containing glass sprayed coating and the corrosion resistant glass sprayed coating forms a molten layer resulting from mutual melting each other.

22. (previously presented): A corrosion resistant member comprising a base material sprayed with a corrosion resistant glass sprayed coating which is an aluminosilicate glass or zirconia silicate glass containing at least one element selected from the group consisting of the group 2a, group 3a and group 4a of the periodic table of elements,

wherein a most superficial layer of the sprayed coating forms a spherical protruded layer in which the concentration of at least one of aluminum or zirconium and elements of the group 2a, group 3a and group 4a is lower than that of an internal sprayed coating.